

Copper-Tin Alloy C92700

| CDA NUMBER | C92700 | |
|---|------------|------------|
| Common Name | 88-10-2-0 | |
| COMPOSITION PERCENT | Min | Max |
| Copper (Cu) | 86 | 89 |
| Tin (Sn) | 9 | 11 |
| Lead (Pb) | 4 | 6 |
| Zinc (Zn) | | 1 |
| Iron (Fe) | | 0.2 |
| Antimony (SB) | | 0.25 |
| Nickel (Ni) | | 2 |
| Sulphur (S) | | 0.05 |
| Phosphorous (P) | | 0.1 |
| Aluminum (Al) | | 0.005 |
| Silicon (Si) | | 0.005 |
| Cu + Sum of Named Elements, 99.3% min. | | |
| In determining Cu min., Cu may be calculated as Cu + Ni. | | |
| Ni value includes Co. | | |
| For continuous castings, P shall be 1.5%, max. | | |
| NEAREST APPLICABLE CASTING STANDARDS | | |
| ASTM (B Series) | B505 | |
| SAE (J Series) | 63 | |
| Federal (QQ-C- Series) | | |
| Military (Mil-C- Series) | | |
| TYPICAL PROPERTIES | Typ | Min |
| Tensile Strength (ksi) | 42 | 35 |
| Yield Strength (.5% extension under load) (ksi) | 21 | |
| Elongation (2 inch gauge length) (%) | 20 | 10 |
| Reduction of Area (%) | | |
| Proportional Limit (ksi) | | |
| Modulus of Elasticity (ksi) | 16000 | |
| Hardness (Brinell) (HB @ 500kg) | 77 | |
| Machinability (% of free cutting brass) | 45 | |
| Fatigue Strength (10 ⁸ cycles) (ksi) | | |
| Impact Strength (Charpy) (ft-lb) | | |
| Impact Strength (Izod) (ft-lb) | | |
| Shear Strength (ksi) | | |
| Compressive Strength (0.001 in. set/in.) (ksi) | | |
| Compressive Strength (0.010 in. set/in.) (ksi) | | |
| Compressive Strength (0.100 in. set/in.) (ksi) | | |
| Creep Strength (0.00001% per hour) (ksi) | | |
| Melting Range (Liquidus-Solidus)(F) | 1800-1550 | |
| Coefficient of Thermal Expansion (per F @ 68-400F) | 0.000010 | |
| Thermal Conductivity (Btu/sq.ft/ft.hr/F @ 68F) | | |
| Specific Heat (Btu/lb/F @ 68F) | 0.09 | |
| Electrical Conductivity (% IACS @ 68F) | 11 | |
| Density (lb/cu.in. @ 68F) | .317 | |
| Pouring Temperature (Light Castings) (F) | | |
| Pouring Temperature (Heavy Castings) (F) | | |
| Patternmakers Shrinkage (in/ft) | 3/16 | |
| Drossing | Low | |
| Gassing | Medium | |
| Fluidity | Medium | |
| Shrinkage | Low | |
| Casting Yield | Medium | |
| Corrosion Resistance: Excellent for hydrocarbons, seawater, food products, and some acids. | | |
| Wear Resistance: Very Good | | |
| Applications: C93200: General utility bearing and bushings, automobile fittings. | | |

Always use the design principles outlined on page two of this information sheet or at our website.

Consult your foundry early in the design process.

This is a high lead alloy. St Paul Brass and Aluminum does not offer it. We can offer low lead alternatives.

